

SILICONE ADHESIVE TAD-G-SI-1C

thermally conductive 1 part / addition cure

TAD-G-SI-1C is a liquid addition cure corrosion-free highly thermally conductive 1 part silicone adhesive. It cures at elevated temperature over 100°C to a strong but still elastic rubber and exhibits excellent primerless adhesion to most surfaces. The adhesive features good thermal conductivity. It allows for being operated at temperatures up to 260°C and does not corrode copper or its alloys when fully cured. It is characterised by high resistance to water, acids, bases and most organic solvents and is especially suitable for applications where high thermal conductivity, adhesion, fast curing and controlled, precision application are essential.



Release 03 / 2020

PROPERTIES

- Thermal conductivity: 1.38 W/mK
- High bonding properties
- Heat addition cure
- Non corrosive
- High operating temperatures up to 260°C
- Extraordinary chemical resistance and longterm stability

AVAILABILITY

- 1 kg jars
- 310 ml cartridges
- Bulk packaging options on request
- Optional with glass beads

APPLICATION EXAMPLES

- LED systems
- Processor cooling
- Memory chip assembly
- CPU board

Technical Data Sheet

PROPERTY	UNIT	TAD-G-SI-1C
MATERIAL		
Colour		Grey
Specific Gravity	g/cm ³	2.06
Linear Shrinkage	%	2.0
Viscosity	Pas	43
Hardness	Shore A	67
Tensile Strength	MPa	3.1
Elongation at Break	%	70
Curing Time (@ 100°C)	min	30
Shelf Life (from Date of Manufacturing, unopened, @ < 15°C)	Months	6
Flammability	UL 94	HB (1.5 mm)
RoHS Conformity	2015 / 863 / EU	Yes
THERMAL		
Thermal Conductivity	W/mK	1.38
Coefficient of Thermal Expansion Volumetric	x 10 ⁻⁶ /K	562
Coefficient of Thermal Expansion linear	x 10 ⁻⁶ /K	187
Operating Temperature Range	°C	- 50 to + 260
ELECTRICAL		
Dielectric Strength	kV/mm	22.5
Volume Resistivity	Ohm - cm	7.7 x 10 ¹⁵
Surface Resistivity	Ohm - cm	1.3 x 10 ¹⁵

All data without warranty and subject to change. Please contact us for further data and information.

All technical data and information are without warranty and believed to be reliable and accurate, corresponding to the latest state of the art. Since the products are not provided to conform with mutually agreed specifications and their use and processing are unknown we cannot guarantee results, freedom from patent infringement, or their suitability for any application. Product testing by the applicant is recommended. We reserve the right of changes.