

# POLYURETHAN POTTING GEL

## TCR-N-PU-2C-LV-AR

dispensable / 2 parts / low viscosity

TCR-N-PU-2C-LV-AR is a 2-part addition cure polyurethan potting compound which is filled with thermally conductive fillers of high temperature stability. It is characterised by very good dielectric and mechanic properties and is suited for encapsulating electric and electronic parts such as transformers, capacitors, inductors, sensors, LEDs and can be moulded or dispensed under normal conditions at room temperature or in vacuum. Its rheologic behaviour allows for usage in geometries that are difficult to access.



Release 12 / 2020

### PROPERTIES

- Polyurethan
- Low viscosity
- 2 part addition cure
- Thermal conductivity: 2.6 W/mK
- Almost zero stress on components
- Dispensable or mouldable
- Solvent-free
- High resistivity against water and humidity
- Free of halogenated flame retardants

### AVAILABILITY

- Tinplate container

### APPLICATION EXAMPLES

Thermal link of:

- Inductors
  - Capacitors
  - LED
  - Battery packs
- For use in Automotive applications  
/ Telecommunication / Controlling  
units / Industrial PCs

Technical Data Sheet

PROPERTY	UNIT	CASTING RESIN	HARDENER
<b>MATERIAL</b>		Polyurethan	Aromatic Isocyanate
Colour		Blue	Brown
Density @ 22 °C	g/cm <sup>3</sup>	2.3 – 2.4	1.20 – 1.25
Mixing Ratio	Weight		100 : 8
Viscosity (@ 22 °C, 10 rpm)	mPas	100,000 – 140,000	15 – 35
Viscosity (Mixed, @ 22 °C, 10 rpm)	mPas		20,000 – 40,000
Hardness	Shore D		40 – 50
Water absorption (30 days @ 23 °C)	%		0.4
Coefficient of Thermal Expansion < T <sub>g</sub> , TMA	1 x 10 <sup>-6</sup> /K		91.4
> T <sub>g</sub> , TMA	1 x 10 <sup>-6</sup> /K		129.1
Curing Shrinkage	%		< 1
Pot Life (100g @ 22 °C / adjustable)	min		10 – 30
Curing Time @ 22 °C / Full chemical hardening	h / days		14 – 24 / 10 – 14
Shelf Life (from Date of Manufacturing, unopened @ 15 – 25 °C)	Months		6
Flammability (Equivalent)	UL 94		VO (4.0 mm)
RoHS Conformity	2015 / 863 / EU		Yes
Class of Insulation			B
<b>TECHNICAL</b>			
Thermal Conductivity	W/mK		2.6
Operating Temperature	°C		- 40 to + 130
Dielectric Strength	kV/mm		31
Volume Resistivity (@ 23 °C, 50% rel. H.)	Ohm - cm		1 x 10 <sup>15</sup>
Dielectric Constant (ε <sub>r</sub> )	@ 50 Hz / 1 kHz / 1 MHz @ 23 °C		5.8 / 5.2 / 4.6
Dielectric Loss Factor (tan δ)	@ 50 Hz @ 23 °C		0.09
Comparative Tracking Index (CTI)			600

All data without warranty and subject to change. Please contact us for further data and information.

All technical data and information are without warranty and believed to be reliable and accurate corresponding to the latest state of the art. Since the products are not provided to conform with mutually agreed specifications, and their use and processing are unknown we cannot guarantee results, freedom from patent infringement, or their suitability for any application. Product testing by the applicant is recommended. We reserve the right of change.